

**Moplen EP500N**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	12	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	27	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Flexural Modulus	1150	MPa	ASTM D 790
Rockwell Hardness	R 95	-	ASTM D 785
Izod Impact notched, 1/8 in	100	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	50	J/m	ASTM D 256
Temperature	-20	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	110	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Features**

Low Warpage, Copolymer, Impact Copolymer

**Applications**

Electrical and Electronical

**Regional Availability**

Asia Pacific, Near East/Africa