

**Moplen EP745T**

PP

LyondellBasell Industries

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>65</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	<b>36</b>	MPa	ISO 527
Flexural modulus	<b>1800</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>2.5</b>	kJ/m <sup>2</sup>	ISO 180/1A
Shore D hardness	<b>68</b>	-	ISO 7619-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>100</b>	°C	ISO 75-1/-2

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Features**

Nucleated, Homopolymer

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

Asia Pacific