

Moplen EP3046

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	70	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1550	MPa	ISO 527
Yield stress	28	MPa	ISO 527
Yield strain	5	%	ISO 527
Strain at break	30	%	ISO 527
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, A	151	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Special Characteristics

Anti-static

Features

Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact

Applications

Packaging, Sports Equipment

Regional Availability

Europe, Asia Pacific, Near East/Africa