

# Moplen HP461Y

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>1300</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Other properties	Value	Unit	Test Standard
Density	<b>900</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Delivery form

Pellets

### Regional Availability

Asia Pacific, Near East/Africa

### Features

Homopolymer