

Moplen HP461Y

PP

PolyMirae

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1300	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Characteristics

Features

Barrier Properties, Color Stability, Good Drawdown, Thermal Stability

Regional Availability

Asia Pacific, Near East/Africa

Applications

Automotive