

# Moplen HP500V

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	120	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	910	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Applications

Packaging

### Special Characteristics

High impact or impact modified

### Regional Availability

Europe

### Features

Homopolymer