

Moplen HP522H

PP

PolyMirae

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	36.3	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Flexural Modulus	1521	MPa	ASTM D 790
Rockwell Hardness	R 98	-	ASTM D 785
Izod Impact notched, 1/8 in	47.1	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	110	°C	ASTM D 648
Vicat Temperature	155	°C	ASTM D 1525
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Features

Barrier Properties, Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

General Purpose

Regional Availability

Asia Pacific, Near East/Africa