

Moplen HP528N

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	34	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1500	MPa	ASTM D 790
Izod Impact notched, 1/8 in	23	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	97	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Blown Film Extrusion, Film Extrusion

Additives

Antiblocking agent

Special Characteristics

Transparent

Features

Tribologic Grade, Homopolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Asia Pacific, Near East/Africa