

Moplen HP560W

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	450	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Characteristics

Processing

Other Extrusion

Features

Barrier Properties, Homopolymer

Delivery form

Pellets

Regional Availability

Europe, Near East/Africa