

Moplen HP623J

PP

PolyMirae

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	35.3	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Flexural Modulus	1521	MPa	ASTM D 790
Rockwell Hardness	R 95	-	ASTM D 785
Izod Impact notched, 1/8 in	37.5	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	108	°C	ASTM D 648
Vicat Temperature	146	°C	ASTM D 1525
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Features**

Barrier Properties, Homopolymer

Regional Availability

Asia Pacific, Near East/Africa