

Moplen HP748H

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	38	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1800	MPa	ASTM D 790
Izod Impact notched, 1/8 in	47	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Sheet Extrusion, Thermoforming

Special Characteristics

Transparent, Opaque

Features

Low Odor, Homopolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Asia Pacific, Near East/Africa