

Moplen PP567P

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	18	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	33	MPa	ISO 527
Yield strain	11	%	ISO 527
Stress at break	21	MPa	ISO 527
Strain at break	700	%	ISO 527
Flexural modulus, 23°C	1150	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	74	°C	ISO 75-1/-2
Vicat softening temperature, A	153	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Other Extrusion

Regional Availability

Europe, Near East/Africa

Features

Gas Fading Resistance, Homopolymer