

Moplen QCP300S

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	35	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1150	MPa	ISO 527
Tensile Strength	26	MPa	ISO 527
Strain at break	25	%	ISO 527
Flexural modulus, 23°C	1100	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Other properties			
Density	915	kg/m ³	ISO 1183
Bulk density	560	kg/m ³	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Features

Copolymer, Impact Copolymer

Certifications

Recycled Resin Content

Applications

General Purpose, Packaging

Regional Availability

Europe