

Moplen RP210G

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Film Extrusion, Sheet Extrusion, Blow Molding, Thermoforming

Certifications

Food contact

Features

High Gloss, Copolymer, Random Copolymer

Applications

Packaging

Chemical Resistance

General Chemical Resistance, Environmental Stress Crack Resistance

Regional Availability

Europe, Near East/Africa