

Moplen RP241H

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	850	MPa	ISO 527
Yield stress	24	MPa	ISO 527
Yield strain	14	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy notched impact strength, +23°C	45	kJ/m ²	ISO 179/1eA
Optical properties			
ASTM Data			
Haze	9	%	ASTM D 1003
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Sheet Extrusion, Blow Molding, Thermoforming

Applications

Packaging

Special Characteristics

High impact or impact modified, Transparent

Regional Availability

Europe

Features

Nucleated, Copolymer, Random Copolymer