

**Moplen RP348N**

PP

PolyMirae

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	28.5	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Flexural Modulus	1177	MPa	ASTM D 790
Rockwell Hardness	R 90	-	ASTM D 785
Izod Impact notched, 1/8 in	47.1	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	95	°C	ASTM D 648
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	15	%	ASTM D 1003
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Transparent

**Features**

Color Stability, Low Odor, Random Copolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Regional Availability**

Asia Pacific, Near East/Africa