

**Moplen RP3469**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	40	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	1100	MPa	ISO 527
Yield stress	20	MPa	ISO 527
Yield strain	14	%	ISO 527
Charpy notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2
Vicat softening temperature, A	127	°C	ISO 306
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	9	%	ASTM D 1003
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Anti-static, Transparent

**Features**

Nucleated, Copolymer, Random Copolymer

**Applications**

Packaging, Sports Equipment

**Regional Availability**

Europe, Near East/Africa