

**Mosten® GB 506**

PP

ORLEN Unipetrol RPA s.r.o.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.9	%	ISO 294-4, 2577
Molding shrinkage, normal	2.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1500	MPa	ISO 527
Yield stress	29	MPa	ISO 527
Yield strain	5	%	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Tensile creep modulus, 1h	1100	MPa	ISO 899-1
Tensile creep modulus, 1000h	580	MPa	ISO 899-1
Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
Shore D hardness	63	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	168	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	57	°C	ISO 75-1/-2

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	200 - 280	°C	-
Mold temperature	20 - 60	°C	-

**Characteristics****Processing**

Injection Molding, Other Extrusion, Thermoforming

**Delivery form**

Pellets, Natural Color

**Features**

Nucleated, Copolymer

**Chemical Resistance**

General Chemical Resistance

**Certifications**

Food contact, Food approval 1935/2004/EC, Food approval 10/2011

**Applications**

General Purpose

**Regional Availability**

Europe