

N00G-01

PP

INEOS Olefins & Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.45	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	24.1	MPa	ASTM D 638
Tensile Strength at Break	27.6	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Elongation at Break	900	%	ASTM D 638
Rockwell Hardness	R 82	-	ASTM D 785
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	92	°C	ASTM D 648
DTUL @ 264 psi	57	°C	ASTM D 648
Vicat Temperature	153	°C	ASTM D 1525
Optical properties			
ASTM Data			
Gloss	56	-	ASTM D 2457
Other properties			
Density	902	kg/m ³	ASTM D 792

Characteristics**Processing**

Pipe/Tube Extrusion, Sheet Extrusion, Blow Molding

Features

Ductile, Copolymer, Impact Copolymer

Special Characteristics

High impact or impact modified

Regional Availability

North America