

**N00N-00**

PP

INEOS Olefins &amp; Polymers

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>0.35</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>33.9</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>26.2</b>	MPa	ASTM D 638
Elongation at Yield	<b>7.91</b>	%	ASTM D 638
Elongation at Break	<b>122</b>	%	ASTM D 638
Rockwell Hardness	<b>R 98</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>N</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>115</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>60</b>	°C	ASTM D 648
Vicat Temperature	<b>160</b>	°C	ASTM D 1525
<b>Optical properties</b>			
<b>ASTM Data</b>			
Gloss	<b>78.2</b>	-	ASTM D 2457
<b>Other properties</b>			
Density	<b>910</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Pipe/Tube Extrusion, Other Extrusion

**Regional Availability**

North America

**Features**

Ductile, Melt Strength, Copolymer, Impact Copolymer