

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	22.6	MPa	ASTM D 638
Tensile Strength at Break	16.5	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Elongation at Break	50	%	ASTM D 638
Rockwell Hardness	R 74	-	ASTM D 785
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	99	°C	ASTM D 648
DTUL @ 264 psi	50	°C	ASTM D 648
Vicat Temperature	145	°C	ASTM D 1525
Optical properties			
ASTM Data			
Gloss	43	-	ASTM D 2457
Other properties			
Density	903	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Special Characteristics

Anti-static, High impact or impact modified

Features

Ductile, Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America