

**NB73I**

PP

Hanwha TotalEnergies Petrochemical co. Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	64.7	MPa	ASTM D 638
Elongation at Break	4	%	ASTM D 638
Flexural Modulus	4415	MPa	ASTM D 790
Rockwell Hardness	R 100	-	ASTM D 785
Izod Impact notched, 1/8 in	118	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	159	°C	ASTM D 648
<b>Other properties</b>			
Density	1100	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Asia Pacific

**Features**

Low Warpage