

Nemcon™ E PP AS

PP

Ovation Polymers

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	740	MPa	ASTM D 638
Tensile Strength at Yield	22	MPa	ASTM D 638
Elongation at Break	170	%	ASTM D 638
Flexural Modulus	525	MPa	ASTM D 790
Izod Impact notched, 1/8 in	93.4	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	3E11	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	920	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Anti-static

Regional Availability

North America

Applications

Electrical and Electronical