

Nemcon™ H PP DP172

PP

Ovation Polymers

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2100	MPa	ASTM D 638
Tensile Strength at Break	20	MPa	ASTM D 638
Elongation at Break	8.5	%	ASTM D 638
Flexural Modulus	700	MPa	ASTM D 790
Izod Impact notched, 1/8 in	42.7	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1150	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

North America