

Network Polymers PP PPB 25 0216

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.4	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	23.4	MPa	ASTM D 638
Elongation at Yield	9	%	ASTM D 638
Izod Impact notched, 1/8 in	854	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Features**

Copolymer

Regional Availability

North America