

Network Polymers PP PPB 25 0802

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26.9	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	90	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ASTM D 792

Characteristics**Features**

Copolymer

Regional Availability

North America