

Osterlene® PPC20-2NA

PP

Osterman's Engineered Polymers Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	26.1	MPa	ASTM D 638
Elongation at Yield	4	%	ASTM D 638
Rockwell Hardness	R 92	-	ASTM D 785
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	104	°C	ASTM D 648

Characteristics**Processing**

Injection Molding

Features

Nucleated, Copolymer, Impact Copolymer

Special Characteristics

Anti-static

Regional Availability

North America