

**Osterlene® PPC50-2**

PP

Osterman's Engineered Polymers Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	50	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	20.4	MPa	ASTM D 638
Elongation at Yield	3.8	%	ASTM D 638
Izod Impact notched, 1/8 in	117	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	96.1	°C	ASTM D 648
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Additives**

Release agent

**Special Characteristics**

High impact or impact modified

**Features**

Thermal Stability, Copolymer, Impact Copolymer

**Applications**

Automotive

**Regional Availability**

North America