

Osterlene® PPH008

PP

Osterman's Engineered Polymers Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.83	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	32	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Izod Impact notched, 1/8 in	51.8	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	83.9	°C	ASTM D 648
DTUL @ 264 psi	51.7	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Features

Melt Strength, Homopolymer

Applications

Automotive

Regional Availability

North America