

Osterlene® PPH35F

PP

Osterman's Engineered Polymers Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Other properties			
Density	902	kg/m ³	ASTM D 792

Characteristics**Processing**

Film Extrusion

Features

Homopolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

North America