

P4G4K-219

PP

Invista

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	12	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	40	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Flexural Modulus	1810	MPa	ASTM D 790
Rockwell Hardness	R 110	-	ASTM D 785
Gardner Impact	1.4	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	40	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	117	°C	ASTM D 648
Melting Temperature	162	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Film Extrusion

Special Characteristics

Transparent

Features

Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR, RoHS compliant

Regional Availability

North America