

**P6G4Z-097**

PP

Invista

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	26	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Flexural Modulus	1186	MPa	ASTM D 790
Rockwell Hardness	R 83	-	ASTM D 785
Gardner Impact	24	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	144	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	88	°C	ASTM D 648
Melting Temperature	162	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	226 - 246	°C	-
Mold temperature	15 - 49	°C	-

**Characteristics****Processing**

Injection Molding

**Certifications**

Food contact, Food approval FDA 21 CFR, RoHS compliant

**Features**

Copolymer, Impact Copolymer

**Regional Availability**

North America