

P6169B-NA

PP

Pontex Polyblend Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	12	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.95	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	15.2	MPa	ASTM D 638
Flexural Modulus	3434	MPa	ASTM D 790
Flexural Strength	31.4	MPa	ASTM D 790
Izod Impact notched, 1/8 in	29.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	130	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1900	kg/m ³	ASTM D 792

Characteristics**Features**

High Gloss

Regional Availability

Asia Pacific