

**PBF3500J**

PP

Itochu Plastics Pte. Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>35</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>25.5</b>	MPa	ASTM D 638
Elongation at Yield	<b>7</b>	%	ASTM D 638
Rockwell Hardness	<b>R 106</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>107</b>	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	<b>80.1</b>	J/m	ASTM D 256
Temperature	<b>0</b>	°C	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>87.8</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>900</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Applications**

Packaging

**Features**

Copolymer, Impact Copolymer

**Regional Availability**

Asia Pacific