

PBS3500J

PP

Itochu Plastics Pte. Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	36	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	19.3	MPa	ASTM D 638
Elongation at Yield	5.5	%	ASTM D 638
Izod Impact notched, 1/8 in	224	J/m	ASTM D 256

Characteristics

Processing

Injection Molding

Features

Nucleated, Copolymer, Impact Copolymer

Special Characteristics

Anti-static, High impact or impact modified

Regional Availability

Asia Pacific