

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0125	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	1724	MPa	ASTM D 638
Tensile Strength	27.6	MPa	ASTM D 638
Flexural Modulus	1379	MPa	ASTM D 790
Flexural Strength	41.4	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256
Electrical properties			
ASTM Data			
Surface Resistivity	9.9E11	Ohm	ASTM D 257
Volume Resistivity	9.9E10	Ohm*cm	ASTM D 257
Other properties			
Density	920	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	79.4	°C	-
Pre-drying - Time	2	h	-
Melt temperature	171 - 204	°C	-
Mold temperature	32.2 - 65.6	°C	-
Injection pressure	48.3 - 75.8	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Anti-static