

PETOPLEN EH 241

PP

Petkim Petrokimya A.S.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	24	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	35.8	MPa	ASTM D 638

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Applications

General Purpose