

**PETOPLEN EH 251**

PP

Petkim Petrokimya A.S.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>24</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>34.3</b>	MPa	ASTM D 638

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Europe

**Applications**

General Purpose