

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>20</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Molding shrinkage, parallel	<b>1.5</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>1.4</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield stress	<b>34</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>1700</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>4.5</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>50</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>90</b>	°C	ISO 75-1/-2
Vicat softening temperature, A	<b>153</b>	°C	ISO 306
Vicat softening temperature, B	<b>90</b>	°C	ISO 306

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>900</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>190 - 230</b>	°C	-
Mold temperature	<b>60 - 80</b>	°C	-

**Characteristics**

<b>Processing</b> Injection Molding, Other Extrusion	<b>Features</b> Homopolymer
<b>Delivery form</b> Natural Color	<b>Regional Availability</b> North America, Europe, South and Central America