

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>8</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Stress at break	<b>19</b>	MPa	ISO 527
Flexural strength	<b>20</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>166</b>	°C	ISO 11357-1/-3
<b>Other properties</b>			
Density	<b>920</b>	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Melt temperature	<b>190 - 230</b>	°C	-
Mold temperature	<b>60 - 80</b>	°C	-

**Characteristics**

**Processing**

Injection Molding, Other Extrusion

**Features**

Homopolymer

**Certifications**

Recycled Resin Content

**Regional Availability**

North America, Europe, South and Central America