

Pexloy PPAT011PR012

PP

Plásticos Novacor Ltda

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	17	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	20	MPa	ASTM D 638

Other properties	Value	Unit	Test Standard
Density	980	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America

Applications

Automotive