

Pexloy PPLT003NC001

PP

Plásticos Novacor Ltda

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 1.3 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Izod Impact notched, 1/8 in | 100 | J/m | ASTM D 256 |

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America

Applications

Automotive