

Pexloy PPLT003PR001

PP

Plásticos Novacor Ltda

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.3	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Izod Impact notched, 1/8 in	100	J/m	ASTM D 256

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America