

**Pexloy PPLT004PR001**

PP

Plásticos Novacor Ltda

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>1.2</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	<b>150</b>	J/m	ASTM D 256
<b>Other properties</b>			
Density	<b>1040</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Regional Availability**

South and Central America