

**Pexloy PPME001PR001**

PP

Plásticos Novacor Ltda

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>5</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	<b>100</b>	J/m	ASTM D 256

**Characteristics****Processing**

Injection Molding

**Regional Availability**

South and Central America

**Applications**

Automotive