

Pexloy PPMT001PR001

PP

Plásticos Novacor Ltda

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	27	MPa	ASTM D 638
Flexural Modulus	1900	MPa	ASTM D 790
Izod Impact notched, 1/8 in	50	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	105	°C	ASTM D 648
DTUL @ 264 psi	60	°C	ASTM D 648
Vicat Temperature	140	°C	ASTM D 1525
Other properties			
Density	1040	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America

Applications

Automotive