

Product Texts**Applications:**

Adhesive tapes, labels, and metallized films, BOPP film by the plan process (stenter) for Food packaging, Flexible packaging (BOPP).

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	33	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Izod Impact notched, 1/8 in	30	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ASTM D 792

Characteristics**Features**

Good Adhesion, Homopolymer

Applications

Packaging

Certifications

Food contact

Regional Availability

North America, Europe, South and Central America