

**Plexar PX6002**

PP

LyondellBasell Industries

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>2.7</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Vicat Temperature	<b>122</b>	°C	ASTM D 1525
<b>Other properties</b>			
Density	<b>892</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Blown Film Extrusion, Film Extrusion, Pipe/Tube Extrusion, Sheet Extrusion, Coating, Blow Molding, Thermoforming

**Delivery form**

Pellets

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa