

Plexar PX6005

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5.4	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Vicat Temperature	140	°C	ASTM D 1525
Other properties			
Density	892	kg/m ³	ASTM D 792

Characteristics**Processing**

Blown Film Extrusion, Film Extrusion, Pipe/Tube Extrusion, Sheet Extrusion, Coating, Blow Molding, Thermoforming

Delivery form

Pellets

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa