

Polimaxx 1100NN

PP

IRPC

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	33	MPa	ASTM D 638
Elongation at Yield	30	%	ASTM D 638
Rockwell Hardness	R 105	-	ASTM D 785

Other Standards ^[5]	Value	Unit	Test Standard
Charpy notched impact strength, +23°C	3	kJ/m ²	DIN 53453

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	95	°C	ASTM D 648

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	190 - 240	°C	-

Characteristics**Processing**

Injection Molding

Features

Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR, RoHS compliant

Applications

General Purpose, Packaging

Regional Availability

Europe, Asia Pacific